

CAUTION NOTICE

Please Note: These bags are NOT soluble and must NOT be added to the mixer. The bags must be split and the contents added to the mixer in a method that avoids any clumping of the Denka CSA powder.

DENKA Power CSA-S MUST NEVER BE ADDED LAST TO THE CONCRETE MIXER

ADD DENKA Power CSA-S INTO THE MIXER FIRST OR SPREAD OVER COARSE AGGREGATE ON THE CONVEYER BELT (IF ACCESS ALLOWS)

Note on Mixing: Results over many years have shown that 10 minutes rapid mixing in the truck is essential to ensure Denka Power CSA-s is uniformly dispersed. Any reduction in this mixing time increases the risk of small pockets of Denka Power CSA-S being present and the formation of small “pop outs” on the slab surface. The extra 10 minutes rapid mixing has been shown to improve the consistency of some concrete properties between truck loads.

Examples of Pop-Outs

